

UNCLASSIFIED

AD _ 406 257 _

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.



GENERAL DYNAMICS | CONVAIR

MODEL
DATE

PAGE
REPORT NO.

Report No. 8926-173

Material - Cobalt Base Alloy - L-605

Spot Weld Strengths

(An Abstract Report)

Abstract:

Spot welding procedures and test results obtained from tests with 0.031" and 0.050" thick L-605 cobalt base alloy sheet are summarized. Pertinent test data are as follows.

<u>Material Thickness and Condition</u>	<u>Tensile</u>	<u>Cross</u>	<u>TS.1</u>
	<u>Shear</u> <u>Strength</u>	<u>Tension</u> <u>Strength</u>	<u>C.T.</u> <u>Ratio</u>
0.031" mill annealed,* welded	1674 lb/spot	894 lb/spot	.53
0.031" weld, heat treat**	1680	706	.42
0.050" mill annealed,* welded	3244	1974	.61
0.050" weld, heat treat**	3290	1081	.33

* 2250°F, water quench

** 1975°F, air cool

Reference: Alesch, C. W., "Material - Cobalt Base Alloy - L-605. Spot Weld Strengths (An Abstract Report)," General Dynamics/Convair Report 8926-173, San Diego, California, 19 April 1963. (Reference attached).



GENERAL DYNAMICS | CONVAIR

MODEL
DATE

PAGE 1
REPORT NO. 8926-173

Report No. 8926-173

Material - Cobalt Base Alloy - L-605

Spot Weld Strengths

(An Abstract Report)

Reference: Vermilyea, E. J., Green, E. D., Carr, W. L., Margitan, E.,
"Fabricability of Materials R-235, L-605, Rene 41, M-252,
and J-1650 as Pertaining to Part No. 8-26054," General
Dynamics/Convair Report AMR-PR 889, San Diego, California,
April 1961.

Annealed, 0.031" and 0.050" thick, mill annealed (2250°F, water quench),
L-605 (Haynes Alloy No. 25, Haynes Stellite Co.) was cleaned by the
methods given in Table 1 and then spot welded. The 0.031" thick sheet
was welded according to the schedule given in Table 2, and the 0.050"
thick according to the Table 3 schedule. The results from tests with
spot welds in mill annealed and re-annealed (1975°F, 30 minutes, rapid
air cool) conditions are shown in Table 4. These data show that spot
weld strengths optimize when mill annealed material is welded without
subsequent heat treatment. Annealing (1975°F, 30 minutes, air cool)
generally reduces weld strengths, especially the cross-tension strength,
and thus contributes to reductions in tension-shear to cross-tension
strength ratios.

Prepared by C. W. Alesch
19 April 1963

MODEL
DATEPAGE 2
REPORT NO. 8926-173

Table 1

Cleaning Method for Annealed R-235

<u>Operation</u>	<u>Cleaning Components</u>	<u>Temp °F</u>	<u>Time (Min.)</u>
Vapor Degrease	Stabilized Tri- chloroethylene (per Mil-T-7003)	180 - 195	1
Alkaline Clean	Oakite 61A, 5-6 ounces per gallon	150 - 180	5
Hot Water Rinse	Steam Condensate	130 - 180	1
Pickle	1.5-20% Hydrofluoric Acid, 25-35% Nitric Acid	Room Temp.	Varied
Water Rinse	Tap Water	Room Temp.	1
Dry	Hot Air	120 - 150	2

Mach. Make SCIAKY Rated Capacity 100 KVA

	Top Sheet	2nd Sheet	3rd Sheet	Electrodes	Top	Bottom
Material	L-605	L-605		RWMA Class and Group	Class 3	Class 3
Gage	0.031"	0.031"		Diameter	5/8 to 1/2	5/8 to 1/2
Condition	as received (annealed)			Contour	4 R	4 R
Material Preparation	chem etch (4104)			SWAC No.		

Throat depth	37	Squeeze cycles	25
Distance between arms	6	Weld interval imp	5
Const. high and vari. press	OFF	Hold cycles	25
Vari. press	OFF	Off cycles	26
Const. low press	ON	Preheat interval imp	4
Co press	ON	Quench cycles	1
Mu. imp	ON	Postheat interval imp	4
Sing. imp	OFF	Quench and postheat	ON
Mult. imp weld	SW	Preheat	ON
With preheat and postheat	ON	Electric contact gauge	52
With current decay	OFF	Pressure gauge 2	53
Tha. group	ON	Pressure gauge 1	28
Th. group	ON	2 tubes	ON
Decades	OFF	1 tube	OFF
Forge delay vernier	OFF	1 or 2 phase	OFF
Forge delay cycles	OFF	3 phase	ON
At beginning of weld interval	ON	Preheat	20
At end of weld interval	OFF	Preheat vernier	0
Forge delay initia. point	SW	Weld	20
Cool cycles	1, 5	Weld vernier	1
Heat cycles	5	Post heat and current decay	20
Current decad. cycles	OFF	Post heat and current decay vernier	1
Current decay	OFF		

Table 2 Resistance Spot Weld Schedule to Weld 0.031 inch L-605 to 0.031 inch L-605
in the Annealed Condition

CONVAIR-SD

Mach. Make Solaky Rated Capacity 100 KVA

	Top Sheet	2nd Sheet	3rd Sheet	Electrodes	Top	Bottom
Material	L-605	L-605				
Gage	0.050	0.050		RWMA Class and Group	II	II
Condition	as received (annealed)			Diameter	1/2	1/2
Material	chem etch			Contour	4 R	4 R
Preparation				SWAC No.		

Throat depth	37	Squeeze cycles	25
Distance between arms	6	Weld interval imp	5
Const. high and vari. press	off	Hold cycles	25
Vari. press	off	Off cycles	26
Const. low press	on	Preheat interval imp	4
Const. press	on	Quench cycles	1
Mult. imp	on	Postheat interval imp	4
Sing. imp	off	Quench and postheat	on
Mult. imp weld	4	Preheat	on
With preheat and postheat	on	Electric contact gauge	60
With current decay	off	Pressure gauge 2	60
Tha. group	on	Pressure gauge 1	27
Th. group	on	2 tubes	on
Decades	0	1 tube	off
Forge delay vernier	0	1 or 2 phase	off
Forge delay cycles	off	3 phase	ON
At beginning of weld interval	on	Preheat	20
At end of weld interval	OFF	Preheat vernier	2
Forge delay initia. point	SW	Weld	20
Cool cycles	1-5	Weld vernier	3
Heat cycles	4.	Post heat and current decay	20
Current decad. cycles	OFF	Post heat and current decay vernier	2
Current decay	OFF		

Table 3 Resistance Spot Weld Schedule to Weld 0.050 inch L-605 to 0.050 inch L-605
in the Annealed Condition

Table 4 Tensile Results of Resistance Spot Welded L-605

Coupon No.	Gage Inches	Tensile Shear Results			Cross Tension Results			Cross Tension to Tensile Shear Ratio	Standard Deviation	
		Annealed Then Weld	Weld Then *Heat Treat	Avg.	Anneal Then Weld	Weld Then *Heat Treat	Avg.		Tensile Shear	Cross Tension
J1	0.031	1700		1674	900		894	53%	63.8	63.1
2	0.031	1710			910					
3	0.031	1740			790					
4	0.031	1640			900					
5	0.031	1580			970					
K1	0.031		1250	1680		770	706	42%	360.5	53.2
2	0.031		2200			690				
3	0.031		1780			640				
4	0.031		1720			750				
5	0.031		1450			680				
L1	0.050	2840		3244	2000		1974	61%	230.9	287.2
2	0.050	3270			2140					
3	0.050	3370			2180					
4	0.050	3340			1475					
5	0.050	3400			2075					
M1	0.050		3320	3290		850	1081	33%	51.4	348.8
2	0.050		3330			950				
3	0.050		3250			960				
4	0.050		3220			1700				
5	0.050		3330			945				

*1975°F 30 Minutes rapid air cool